



DATA SHEET

Filter media

Polyester + PTFE Coating

Polyester + PTFE Coating

Appearance	White
Use	Pleatable filter media
Composition	100% Polyester Spunbonded +PTFE coating
Area weight (g/m²)	270
Thickness (mm)	0.60
Air Permeability (m³/m²/h - 200 PA)	1100
Surface electrical resistance (Ohm)	-
IFA/BIA certificate (DIN EN 60335-2-69:2008)	M
Max. working temperature (C°)	150
Volume of pores (%)	66
Application field	Laser cutting fumes, plasma cutting fumes, oxygen-cutting fumes, sand cement, rich steel welding fumes, food powder, cement, milk powder.